

Technical data sheet

MPD

**INDUSTRIES PVT. LTD** 

Page 1 of 2

# Mixed Fatty Acid Fast Drying Alkyd Resin Economy

### Description

ALK 3936 55 is short oil oxidising modified polyester resin for economical air drying applications and low bake systems for darker shades.

### Suggested uses

Dark Shades Vehicle refinishes Fast Drying industrial finishes

Low Bake forced drying products

Heavy duty primers

# Compatibility

Short Oil Alkyd Less Compatible
Medium Oil Alkyds Less Compatible
Amino Resins Less Compatible
Long Oil Alkyds Incompatible
Cholorinated Rubber Incompatible
NC Resins Incompatible
Vinyl Resins Incompatible

### Solubility / Thinnability

Aromatic Hydrocarbons

**Esters** 

Ketones

Limited solubility in Alcohols

Insoluble in Aliphatic hydrocarbon

#### **Performance**

Excellent Colour and colour retention Excellent Gloss and gloss retention Good Re-coatability Good adhesion to metal surface. Rapid Air drying

# ALK 3936 55 Typical Physical and Chemical Properties

Solvent **Xylene** Oil Lenghth in % 28 Acid Value (mg Koh/gm)Max. 15 Reducer 50 % in Xylene Colour Dark Brown 4000 - 5500 Viscosity in C.Ps@ 25 C (55 % Sol) Viscosity @30°C in sec. B4 ford cup 300 - 350 Gardener Viscosity (50 % Solution) X - 7 Solid Contents in %, 120 C/1 Hr. 54 - 56 Oh Value on resin solid basis 98

### Recommendations

In air drying systems 0.05 % CO, 0.5 % Pb ,0.1 % Ca calcu as metal on solid resins content are recommended in air dr systems. In lead free systems use 0.2% - 0.6% of Zirconiur can be used as an alternative to Lead.

Surface dry 15 Minutes
Tack free 120 Minutes
Hard dry Overnight

In low bake system recommended level of Melamine Formaldehyde is 5-15% on solid resin basis are added and then baked at 80c.

Version 01 Date of issue:01/01/13

MPD Industries P.Ltd.
Tel: 91-731-2720325, 2720775 Fax: 91-731-2720136
E-mail: info@mpdyechem.com Web: www.mpdyechem.com

Supersedes: \_



Technical data sheet

MPD

**INDUSTRIES PVT. LTD** 

Page 2 of 2

### **Storage**

It should be stored indoors in the original, unopened and undamaged containers in a dry Place at storage temperatures between 5°C&30°C. Exposure to sun shine should be avoided

# **Stability**

Under the above-mentioned storage conditions the Stability of the resin will be 24 months ex-work

# **Packing Codes**

PAC 1000 Bulk tankers Mild steel

PAC 0011 Iso Tank

PAC 1011 Steel Closed head drums 200 Kgs net

PAC 5011 Second hand Steel Closed head drums 200 Kgs

\* Special packing also available on request

Supersedes: \_\_\_