

Glycerine Ester Gum

Description

EST 5511 99 is a Glycerine ester of Gum Rosin.

EST 5511 99 Typical Physical and Chemical Properties

Suggested uses

Wax systems in hot melt adhesives
 Synthetic floor tile adhesives
 Adhesives
 Compatible with vinyl co - polymers

% Non Volatile Content	100
Softening Point Ball & Ring °C	85 - 95
Acid Value (mg Koh/gm)Max.	7
Reducer	50 % in Toluene
Colour in Gardner Scale Maximum	
50 % solution	12
Viscosity in FCB4 @ 25 °C	
50 % solution	13 - 17
MTO /WS Tolerance Minimum	1 - ∞

Storage

The large contact surface the pieces of resin present make them susceptible to gradual oxidation, which can be more advanced in some batches than others. This can cause darkening.

Therefore, we strongly recommend keeping strict control of inventories at all times, and taking special care to ensure that the oldest material is used first. We suggest a shelf life of 1 year for this product.

Packing Codes

PAC 3010	HDPE Wovensack	Net 25 Kgs.
PAC 3011	Paper Laminted HDPE Bag	Net 25 Kgs.
PAC 3015	Jumbobag HDPE Wovensack	Net 300 Kgs
PAC 3020	Jumbobag HDPE Wovensack	Net 500 Kgs

* Special packing also available on request

Version 01

Date of issue:01/01/13 Supersedes : __

MPD Industries P.Ltd.

Tel : 91-731-2720325, 2720775 Fax : 91-731-2720136

E-mail : info@mpdyechem.com Web : www.mpdyechem.com

The information in this bulletin is believed to be accurate, but all recommendations are made without warranty since the conditions of use are beyond MPD Industries control. The listed properties are illustrative only, and not product specifications. MPD Industries Pvt .Ltd. disclaims any liability in connection with the use of the information and does not warrant against infringement by reason of the use of its products in combination with other material or in any process