

Technical data sheet

MPD Industries P Ltd.

Page 1 of 1

TRIPROPYLENE GLYCOL DIACRYLATE

Description

UVP 0201, Tripropylene Glycol diacrylate (TPGDA) is a Difunctional monomers, which polymerize when, expose to sources of free radicals. It is compatible with a wide range of acrylated resins. It is low odour and good flexible monomer.

Product Highlights

Low Volatility and viscosity. Light Colour **High Reactivity**

Performance Verification

Good cure speed without brittleness Good Solvent and abrasion resistence Good Chemical resistence Good Flexibilty

Suggested Applications

Adhesives for paper lamination.

Photopolymers

Over print Varnish

Wood Coatings

Wood fillers and topcoats

Lithographic inks

Screen Printing Inks

Coatings

Photoresists

Solder Marks

Version 01

Date of issue:01/01/13 MPD Industries P.Ltd.

Supersedes: ___

Tel: 91-731-3299031,2973326 E-mail: info@mpdyechem.com Web: www.mpdyechem.com

UVP 0201 Typical Physical and Chemical Properties

Appearance Colour in Gardner scale Maximum Acid Value mg Koh/g maximum	Clear Liquid 1 1
Viscosity @ 25 C in Cps	15
Viscosity by FCB4 30 C	14 + - 2
Functionality	2
Molecular Weight	300
Density g/Cm3	1.03 +- 0.01
Refractive index	1.4485
Tg C	62
Surface Tension dynes/cm	33.3

Storage And Handling

Should be stored in cool dark place, Avoid direct sunlight exposure on the stored /in use material. Please refer to Material safety data sheet for more information regarding storage and handling conditions.

PACKING CODES

PAC 0115 Polyethylene closed head drums Black 200 Kgs PAC 0122 Polyethylene closed head drums Black 90 Kgs PAC 0132 Polyethylene closed head drums Black 50 Kgs PAC 0141 Polyethylene closed head drums Black 20 Kgs

The information in this bulletin is believed to be accurate, but all recommendations are made without warranty since the conditions of use are beyond MPD Industries control. The listed properties are illustrative only, and not product specifications. MPD Industries Pvt .Ltd. disclaims any liability in connection with the use of the information and does not warrant against infringement by reason of the use of its products in combination with other material or in any process